



EMSL Analytical, Inc.

107 Haddon Avenue, Westmont, NJ 08108
Phone: (856) 858-4800

Attn.: **Chris Tracy**
Twin-Chem, Inc.
5010 Hickory Hills Drive
Woodstock, GA 30188

Phone: 770-924-5333 Fax: 770-924-6147

EMSL Case No.: 3604000672
Sample(s) Received: 1/26/04
Date of Analysis: 01/27/04
Date Printed: 01/28/04
Reported By: M. Sillick

Project ID: Concrete Protector

Laboratory Report

The samples reported herein have been analyzed per the following equipment and methodologies.

Methods & Equipment: ASTM C1028¹ Standard Test Method for Determining the Static Coefficient of Friction of Ceramic Tile and Other Like Surfaces by the Horizontal Dynamometer Pull-Meter Method.

Descriptions & Definitions: 1. Because Standard Tiles for ASTM C1028 are not commercially available, the static coefficient of friction values are reported without a calibration correction.

Analyzed by:

Matthew Sillick
Materials Science Analyst

January 27, 2004

Date

QC :

Bruce Benjamin
Market Development Director

January 28, 2004

Date

The results are obtained using the methods and sampling procedures as described in the report or as stated in the published standard methods, and are only guaranteed to the accuracy and precision consistent with the used methods and sampling procedures. Any change in methods and sampling procedure may generate substantially different results. EMSL Analytical, Inc. assumes no responsibility or liability for the manner in which the results are used or interpreted.



Attn.: **Chris Tracy**
Twin-Chem, Inc.
5010 Hickory Hills Drive
Woodstock, GA 30188

Phone: 770-924-5333 Fax: 770-924-6147

EMSL Case No.: 3604000672
Sample(s) Received: 1/26/04
Date of Analysis: 01/27/04
Date Printed: 01/28/04
Reported By: M. Sillick

Project ID: Concrete Protector

Laboratory Report

Table 1. Coefficient of Friction

<i>Sample ID</i>	<i>Average</i>	<i>Standard Deviation</i>
Dry Coefficient of Friction		
FS1	0.658	0.061
Behr	0.633	0.046
Wet Coefficient of Friction		
FS1	0.639	0.029
Behr	0.675	0.056

Test samples were analyzed as received.